

	Specification/Test	PURE-Coat™ Siloxane	Test Laboratory
1	Salt spray ASTM B-117	10,000 Hours	COT // Dercom
2	Acetic salt spray ASTM-G85 annex 5 prohesion	3,000 Hour40 cycles	COT // Dercom
3	Sulphuric acid Kesternich SFW 2,0 S	4,200 Hours	COT
4	Ozone humidity cycle exchange ISO-20340	>500 cycles	COT
5	ASTM D-4060 Taber Abraser wear test	passed	COT // Dercom
6	Humidity ASTM D2247-99	G0/5B	Dercom
7	Adhesion B-3359 to aluminum and copper	passed	Dercom
8	Pencil Hardness BH aluminum and copper	passed	Dercom
9	Impact LBS 100/sq inch ASTM D-2794	passed	Dercom
10	Immersion D-870-92 1000 hours	passed	Dercom
11	Mandrel Bend: 1/8 inch ASTM D-522/93A	passed	Dercom
12	Heat resistance 360 C 4 hours/-42c 9 days	passed	Dercom
13	ISO-12944 C5 compliance staement	Compliant	Internal
14	Stainless steel multi mastic comparasion	Compliant	Internal
15	Humid SO2 and CO2 test NEMA 4X LIL UL-1332	Compliant	Internal